

LRF150R Release Film

■ Product description

LRF150 is economical, high elongation release film.

LRF150 exhibits excellent release characteristics and vertical strength resistance, commonly used in resin infusion process.

This release film is supplied in both perforated and non-peforated versions. Standard perforations are P3 & P6 & P16 & P31 but other perforations might be possible under request, please ask our technical team.

■ PROPERTIES

Maximum Use Temperature	302 °F (150°C)	
Colour	Red	
Tensile Strengt(MD)/MPa	ASTM D882	≥ 55
Tensile Strengt(TD)/MPa		≥ 30
Elongation(MD)/%	ASTM D882	≥ 500
Elongation(TD)/%		≥ 600

■ AVAILABILITY&PACKAGING

Standard Widths	1.3m, 1.5m (50", 60")
Standard Length	500m, 1000m (1640',3280')

■ Notes

Store in cool, dry place, and avoid direct sunlight

No skin irritation problems and no other special requirement.