



FOUNDRY PRODUCTS: Technical Data Sheet

PRODUCT: No-Bake Acid Cured Phenolic Resin - Resital 1996

mical Data

DESCRIPTION:

A phenol-formaldehyde based resin, clear and reddish-brown in colour with a low nitrogen content. A very low odour resin, used commonly for large and medium sized castings.

FIELD OF APPLICATION

Cores and molds for steel and iron castings. It is particularly suitable for use with reclaimed foundry sands. Exceptionally good performance for very large, thick and heavy section castings. Exhibits superior thru-cure properties which makes it an excellent resin for core making operations. Contains a proprietary additive that helps in improved stripping and flexibility in mold handling.

PHYSICAL AND CHEMICAL PROPERTIES **

Specific Gravity @ 25°C Viscosity @ 25°C Free Formaldehyde Water Content 1.180 - 1.2075 kg/l 50- 150 cps 0.1 % max 14.5 - 15.5 %

METHOD OF APPLICATION

It is generally used at 0.9-1.6% based on sand. Levels of 0.8~% are obtained in foundries with good sand control. When using cold, dusty or new sand, levels of 1.5% may be necessary. Hardening is obtained with one of the following catalysts:

Catasol H 962 / N 960 are typically recommended

SHELF LIFE: Good for one months if not stored in direct sunlight. Do not let this product heat up over 30 deg C.

SAFETY MEASURES

Resin and catalyst are to come in contact only in the presence of sand; without the sand a violent reaction takes place. Never store resins in containers that have stored catalysts or other acids and vice versa. It is recommended that the sand/catalyst/resin mixture be handled using rubber gloves to avoid loss of natural oils in the skin.

^{**} The information presented, while not guaranteed, it is to the best of our knowledge true and accurate. No warranty or guarantee, express or implied, is made regarding the performance or stability of any product, since the manner of use and conditions of storage and handling are beyond our control. No suggestions for product use are intended as and nothing herein shall be construed as a recommendation to infringe any existing patents or to violate any government laws.

